

**Listing of Claims:**

1. (Previously Presented) A powder batch comprising composite electrocatalyst particles, said electrocatalyst particles comprising a support phase and an active species phase dispersed on said support phase, wherein said support phase comprises primary support particles having an average size of from about 10 to about 100 nanometers, wherein the average cluster size of said active species phase is not greater than about 20 nanometers and wherein said electrocatalyst particles have a surface area of at least about 90 m<sup>2</sup>/g and an average particle size of at least about 0.3  $\mu$ m.
2. (Original) A powder batch as recited in Claim 1, wherein said active species phase has an average cluster size of from about 0.5 nanometers to about 5 nanometers.
3. (Original) A powder batch as recited in Claim 1, wherein at least about 50 percent of said active species phase has a cluster size of not greater than about 3 nanometers.
4. (Original) A powder batch as recited in Claim 1, wherein said active species phase comprises a metal.
5. (Original) A powder batch as recited in Claim 1, wherein said active species phase comprises a platinum group metal.
6. (Original) A powder batch as recited in Claim 1, wherein said active species phase comprises a metal oxide.
7. (Original) A powder batch as recited in Claim 1, wherein said active species phase comprises a transition metal oxide.
8. (Original) A powder batch as recited in Claim 1, wherein said active species phase comprises manganese oxide.
9. (Original) A powder batch as recited in Claim 1, wherein said electrocatalyst particles have a surface area of at least about 200 m<sup>2</sup>/g.
10. (Original) A powder batch as recited in Claim 1, wherein said primary support particles comprise carbon.
11. (Original) A powder batch as recited in Claim 1, wherein said primary support particles comprise graphitic carbon.

12. (Original) A powder batch as recited in Claim 1, wherein said electrocatalyst particles have an average particle size of not greater than about 10  $\mu\text{m}$ .

13. (Original) A powder batch as recited in Claim 1, wherein said electrocatalyst particles have an average particle size of from about 1  $\mu\text{m}$  to about 10  $\mu\text{m}$ .

14. (Original) A powder batch as recited in Claim 1, wherein said electrocatalyst particles are substantially spherical.

15. (Original) A powder batch as recited in Claim 1, wherein said electrocatalyst particles comprise from about 20 to about 40 weight percent of said active species phase.

16. (Original) A powder batch as recited in Claim 1, wherein said electrocatalyst particles have a porosity of at least about 40 percent.

17. (Previously Presented) A powder batch of metal-carbon composite electrocatalyst particles, said electrocatalyst particles comprising a carbon support phase and a metal active species phase dispersed on said support phase, wherein said support phase comprises primary carbon support particles having an average size of from about 20 to about 40 nanometers and wherein the average cluster size of said metallic active species phase is not greater than about 10 nanometers and wherein the average particle size of the electrocatalyst particles is at least about 0.5  $\mu\text{m}$ .

18. (Original) A powder batch as recited in Claim 17, wherein said metallic active species phase comprises a platinum group metal.

19. (Original) A powder batch as recited in Claim 17, wherein said metallic active species phase comprises platinum metal.

20. (Original) A powder batch as recited in Claim 17, wherein said active species phase comprises a metal alloy.

21. (Original) A powder batch as recited in Claim 17, wherein said electrocatalyst powders have a surface area of at least about 200  $\text{m}^2/\text{g}$ .

22. (Original) A powder batch as recited in Claim 17, wherein said electrocatalyst powders have a porosity of at least about 40 percent.

23. (Original) A powder batch as recited in Claim 17, wherein at least about 50 weight percent of said active species phase has a cluster size of not greater than about 3

nanometers.

Claims 24-28 (Cancelled).

29. (Previously Presented) A method for the production of composite electrocatalyst particles, comprising the steps of:

a) generating an aerosol of droplets from a precursor liquid using a two-fluid nozzle wherein said precursor liquid comprises at least a first precursor to a support phase, said first precursor comprising particulate carbon, and at least a second precursor to an active species phase;

b) moving said droplets in a carrier gas; and

c) heating said droplets to remove liquid therefrom and react at least one of said first and second precursors to form composite electrocatalyst particles wherein said active species phase is dispersed on said support phase.

30. (Original) A method as recited in Claim 29, wherein said carrier gas is air.

31. (Original) A method as recited in Claim 29, wherein said carrier gas is nitrogen.

32. (Original) A method as recited in Claim 29, wherein said heating step comprises passing said droplets through a heating zone having a reaction temperature of not greater than about 400°C.

33. (Original) A method as recited in Claim 29, wherein said heating step comprises passing said droplets through a heating zone having a reaction temperature of not greater than about 300°C.

34. (Original) A method as recited in Claim 29, wherein said active species phase is a metal and wherein said precursor liquid further comprises a reducing agent.

35. (Original) A method as recited in Claim 29, wherein said active species phase is a metal oxide and wherein said precursor liquid further comprises an oxidizing agent.

36. (Cancelled)

37. (Original) A method as recited in Claim 29, wherein said first precursor comprises particulate carbon having a surface area of at least about 200 m<sup>2</sup>/g.

38. (Original) A method as recited in Claim 29, wherein said first precursor comprises particulate carbon having an average size of from about 20 to about 40 nanometers.

39-81. (Cancelled)

82. (Previously Presented) A powder batch as recited in Claim 1, wherein said electrocatalyst particles have an average particle size of not greater than about 20  $\mu\text{m}$ .

83. (Previously Presented) A powder batch as recited in Claim 17, wherein said electrocatalyst particles have an average particle size of not greater than about 20  $\mu\text{m}$ .